




| DESCRIPTION | | | |
|--|-----------------------------|--------------------|---|
| Total Thickness | EN ISO 24346 (EN 428) | mm | 9.5 |
| Weight | EN ISO 23997 (EN 430) | g/m ² | 9880 |
| Size | EN ISO 24342 (EN 427) | mm | 229x1235 / 298x620 |
| CLASSIFICATION | | | |
| Norm/Product Specification | - | - | EN 16511 |
| European Classification | EN ISO 10874 (EN 685) | class | 32 |
| Fire Rating | EN 13 501-1 | class | Bfl-s1 |
| Static Electrical Propensity | EN 1815 | kV | < 2 |
| Slip Resistance Wet | DIN 51130 | class | R10 |
| PERFORMANCES | | | |
| Impact sound insulation | EN ISO 717-2 | dB | 16 |
| Dimensional Stability | EN ISO 23999 (EN 434) | % | ≤ 0.15 |
| Residual Indentation | EN ISO 24343-1 (EN 433) | mm | ≤ 0.10 |
| Castor chair test | ISO 4918 (EN 425) | - | OK |
| Thermal Conductivity | EN ISO 10456 (EN 12 524) | W/(m.K) | 0.25 |
| Colour Fastness | EN 20 105 - B02 | degree | ≥ 6 |
| Surface Treatment | - | - | PUR+ |
| Chemical Products Resistance | EN ISO 26987 (EN 423) | | OK |
| ENVIRONMENT / INDOOR AIR QUALITY | | | |
| TVOC after 28 days | ISO 16000-6 | µg/ m ³ | < 100 |
| CE MARKING | | | |
|  | EN 14041 | |  |
| | | |  |